

Adfil®Sinta M2219

Synthetic Micro Fiber

DESCRIPTION

Adfil®Sinta M2219 is a synthetic fiber for concrete, manufactured from 100% virgin polypropylene in a micro-monofilament form. Adfil®Sinta M2219 is produced on a state-of-the-art production line which is specifically designed to yield an ultrathin concrete reinforcing fiber able to achieve superior performance at a lower dosage rate compared to conventional monofilament fibers. Adfil®Sinta M2219 contains over 70 million individual fibers for each 1.0 lb/yd³ dosed. Engineered specifically for use in concrete, they are alkali resistant, non-absorptive and completely non-corrosive. Adfil®Sinta M2219 protects concrete from stresses which cause cracking while the concrete is most vulnerable during the first 24 hours after placement. Adfil®Sinta M2219 complies with ASTM C1116, Standard Specification for Fiber-Reinforced Concrete and Shotcrete, Type III Synthetic Fiber-Reinforced Concrete or Shotcrete. Adfil®Sinta M2219 is available in 19 mm (0.75 in.) length. Adfil®Sinta M2219 uniformly distributes multi-dimensionally throughout the concrete mixture. The extremely high number of fibers in the fresh concrete matrix protects the concrete when its tensile strength is lowest, reducing the formation of plastic shrinkage cracking.

The reinforcement reduces the formation of all types of early age cracking.

This cracking caused by plastic shrinkage, settlement and other internal stresses would otherwise permanently weaken the resultant concrete. The concrete permeability is decreased, while surface characteristics, impact and toughness properties are improved.

When tested in accordance with ICC ES AC32 criteria for plastic shrinkage crack reduction, Adfil®Sinta M2219 fibers provided a 78% reduction in plastic shrinkage cracking over a control sample when dosed at 0.5 pcy.

Technically advanced production techniques make Adfil®Sinta M2219 a highly durable fiber that is virtually invisible in fresh concrete. This minimizes fiber-reinforced concrete finishing concerns while providing the highest level of crack protection available.

ADVANTAGES

- Protects concrete when tensile strength is at its lowest, reducing the formation of plastic shrinkage cracking.
- Enhances impact and toughness properties.
- Easy to mix and fast to disperse.
- Minimizes fiber-reinforced concrete finishing concerns.
- Reduces plastic shrinkage cracking and improves durability.
- Protects concrete from stresses that cause cracking.
- Provides cost effective control of plastic shrinkage.
- Provides overall higher quality of concrete.

FIELDS OF APPLICATION

- Specifically, such applications include but are not limited to, slabs on grade, pavements, overlays, sloped walls, pools, shotcrete, stucco, precast, and prestressed products.
- It is suggested that this product be used in conjunction with properly compacted base materials and jointing in accordance with ACI guidelines and standards.

Method of Use

Dosage

- Adfil®Sinta M2219 may be added to concrete at any point during the batching or mixing process. Adfil®Sinta M2219 may be added to the aggregate during weighing or charging, or to the central mixer or truck before, during, or after charging. The concrete must be mixed at high speed for 5 minutes, or 70 revolutions, after the addition of Adfil®Sinta M2219 to ensure uniform distribution. The standard range of addition for Adfil®Sinta M2219 is 300 to 600 g/m³ (0.5 to 1.0 lb/yd³) of concrete.
- ASTM C1579 testing has shown that 300 g/m³ (0.5 lb/yd³) is most efficient, providing greater than 77% crack reduction when compared to the control specimen.

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users.

Adfil® Sinta M2219

Synthetic Micro Fiber

Additional Usage Recommendations

- Adfil® Sinta M2219 may be used as an alternative to light-gage welded-wire reinforcement in applications where decreased plastic shrinkage cracking and improved durability are desired.
- Specifically, such applications include but are not limited to: slabs on grade, pavements, overlays, sloped walls, pools, shotcrete, stucco, precast, and prestressed products. It is suggested that this product be used in conjunction with properly compacted base materials and jointing in accordance with ACI guidelines and standards.

Complimentary Products

- Adfil® Sinta M2219 is compatible with all admixtures. Its action in concrete is purely mechanical and will not affect the hydration process. Each admixture should be added separately.

Process Component

- Fibers shall be 19 mm (0.75 in.) micro-monofilament polypropylene fibers.
- 450 grams (one pound) of fibers shall contain no less than 70 million individual fibers, 225 grams (0.5 lb) of fibers shall contain no less than 35 million individual fibers.
- Required dosage rate shall be as specified by the design engineer or architect.
- Adfil® Sinta M2219 shall be used in strict accordance with the supplier's recommendations and within time as specified in ASTM C94. The fiber shall comply with ASTM Designation C1116 Type III. Standard ACI 302 procedures for placing, finishing and curing shall be followed when using Adfil® Sinta M2219.

CHARACTERISTICS

Product Nature	Polypropylene fibers
Specific gravity (25°C)	0,910
Fiber length	19 mm
Ignition Point	590 °C
Tensile strength	290 MPa
Elasticity module	3 GPa
Melting Point	160 °C
Chemical resistance	High

PRECAUTIONS

- Read and understand the product label and Safety Data Sheet (SDS).
- All users should acquaint themselves with this information prior to working with the products and follow the precautionary statements.

SAFETY

Prior to any use, please read carefully the Safety Data Sheet.

PACKAGING

- 600g fiber box

ADDITIONAL CERTIFICATIONS & MARKINGS

- ASTM C1116 / C1116M, Standard Specification for Fiber-Reinforced Concrete, Type III Synthetic Fiber-Reinforced Concrete
- Meets ICC ES AC308 criteria for Plastic Shrinkage Crack Reduction
- BOCA National Building Codes, SBCCI Standard Building Code, ICBO Uniform Building Code and all supplements as adopted by the Council of American Building Officials.
- ACI 544.1 R State of the Art Report of Fiber-Reinforced Concrete

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users.

Adfil® Sinta M2219

Synthetic Micro Fiber

Chryso
Concrete
Solutions

07/14/2025

- ACI 302 Guide for Concrete Floor and Slab Construction
- ASTM C1116 Standard Specification for Fiber-Reinforced Concrete and Shotcrete.
- ASTM C1579 Standard Test Method for Evaluating Plastic Shrinkage Cracking of Restrained Fiber Reinforced Concrete (Using a Steel Form Insert).
- ASTM C94 Standard Specification for Ready-Mixed Concrete.
- Underwriters Laboratory (UL) Series D700 and D800 metal deck assemblies

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users.